

A quick drying, low odour, water thinned primer/finish coat, with excellent adhesion, stain blocking and anticorrosive properties.

Recommended Areas of Use

For use as a quick drying adhesion promoting, stain blocking and anticorrosive coating on ferrous metals, non-ferrous metals, common plastics (e.g. melamine and uPVC), ceramic tiles, glass, wood and existing painted surfaces.

Certificates & Approvals

Manufactured under the auspices of an ISO 9001:2008 quality & ISO 14001:2004 environmental management systems.

2004/42/EC EU limit value for this product (cat. A/b wb): 100g/l (2010). This product contains max 30 g/l VOC.

Properties

Gloss	Eggshell (approx. 25%)	Surface dry	30 Minutes
Theoretical Coverage	11 m ² /L/coat	Minimum over coating time	1 hour minimum*
Recommended number of coats	2 coats minimum as a finish	Maximum over coating time	Unlimited
Density	1.24 kg/L	Minimum application conditions	10°C or above for application (minimum of 3°C above dew point)
Volume solids	41%	Full Cure	7 days
Flash point (Abel closed cup)	Non-Flammable	Shelf life	2 years minimum in original unopened containers.
VOC	30 g/L	Colour range	RAL, British Standard
Thinner / Cleaning	Water		
Recommended wet film thickness	75-100 microns/coat	Recommended dry film thickness	35 microns/coat

Suitable Surfaces

Suitable for use over most properly cleaned and prepared interior and exterior commercial wood, plastic and metals. Compatibility with existing coatings should be confirmed by preparing and painting a test patch. Anticorrosive for application to ferrous and non-ferrous metals that have been fully and properly prepared. Seals most stains in the primer coat including water, nicotine, hardwood resin bleed, bitumen.

Application Information

*Drying times will be prolonged at lower temperatures and over application.

All surfaces must be dry and dust free before coating. Application should always conform with the codes of practice described in BS 6150 and BS 5493

Brush and Roller - supplied ready for use. Thin with 0-5% Water if required.

Conventional Air Spraying - Thin with 5-15% water as required. Tip size - 2.0mm. Tip pressure - 60psi (0.4MPa) approximately.

Airless Spraying - Thin with 0-10% water as required. Tip size - 19 thou (0.48mm) approximately
Tip pressure - 2100 psi (15MPa) approximately.

Cleaning

Equipment should be cleaned immediately after use with water.

Specifications

Surface Preparation

Stain locking: Encapsulates stains in the primer coat, application of second coat will be required to hide and in extreme cases a third. One Can should be allowed to hard dry prior to overcoating this will take at least one hour, over application may result in longer drying times

Aluminum, stainless steel, galvanised steel, copper and other metals: cleaned and degreased with methylated spirit, and lightly abraded if possible. White salts on weathered galvanising must be removed during cleaning and degreasing. Light surface rusting can be treated with Bradite Rust Convertor RC46. Heavy rusting to be removed to clean metallic finish (SIS-St 3).

New Wood: Ensure moisture content of the timber is below 15% before commencing application. Damp wood should never be painted as this may give rise to blistering, flaking, cracking and premature coating failure.

Hard Woods: Wipe with methylated spirit to remove excess resin, changing the face of the cloth regularly. Lightly abrade.

Green oak: should not be painted unless it has been weathered for at least 6 months.

Powder coated, Varnish and Existing paint finish: Remove all loose and flaking paintwork. Degrease using Bradite TD39 Industrial Degreaser, followed by clean water rinse. Rub down thoroughly with a medium grade sand paper to provide a key and a defect free smooth surface, "feathering in" areas where paint has been removed.

UPVC, Formica, Melamine and Plastics: For long term performance, degrease using methylated spirit & lightly abrade surfaces.

New plaster walls: For plaster skim, allow at least four weeks for the plaster to thoroughly dry. Apply a primer coat by thinning the paint with a 5 to 25% (v/v) addition of clean water, depending upon the porosity of the substrate. Cut in by brushing at the same dilution recommendation as for priming, to promote flow and sealing of the substrate.

For new, fully plastered walls, allow at least six months for the plaster to thoroughly dry before painting. This product is not recommended for painting lime or other natural plasters.

Painting System

1st coat	Bradite ONE CAN OC64
2nd coat	Bradite ONE CAN OC64
3rd coat	Bradite ONE CAN OC64 [If required]

Summary Safety Information

Always refer to the Health and Safety sheet for the product before use, and observe the warning phrases on the label. In general, avoid inhalation of spray mist and skin contact by the use of masks, gloves and other personal protection. Eyes should be copiously washed with water or proprietary wash, and medical attention obtained. Skin should be thoroughly washed using a cleanser and soap and water.

Disclaimer - The information on this data sheet is correct to the best of our knowledge and experience. Bradite reserves the right to modify data contained herein, without notice. The information supplied does not absolve users from responsibility to carry out their own tests and experiments, nor does it imply any legally binding assurance of certain properties or suitability for any specific purpose. Conditions of service and application may be beyond our control, so no liability whatsoever can be accepted on the basis of the information supplied herein.